

Vertical linear joint in metal stud		7.9
Fire Resistance Test In Accordance With EN 1366-4 / metal stud wall 100 mm		
Linear joint 100 mm width	Firetect Silicone sealant 100 x 10 mm (wxd) on exposed side	EI 60 minutes
opening 100 mm x 900 mm	and rock wool backing 100 x 50 mm <i>density 50 kg/m³</i>	

